

PDY-132

(Super Yellow)

Function: Polymer Yellow


Features:

- Soluble PPV copolymer
- Excellent reproducibility
- Broad emission spectrum
- Very high efficiency
- Very low operating voltage / for PM 100.000 cd/m² pulsed <10V
- Very long DC and AC lifetime

Standard device stack ²⁾

Ag	150 nm
Ba	6 nm
PDY-132	80 nm
Pedot ³⁾	20 nm
ITO/Anode	

Typical LIV & efficiency curves ¹⁾ measured in a standard device stack ²⁾




Typical performance ¹⁾ measured in a standard device stack ²⁾

	Typical Value ¹
Max. Efficiency	11 cd/A
Onset Voltage	2.2 V
Voltage at 100cd/m ²	3.0 V
Voltage at 1000cd/m ²	4.3 V
Max. Power Efficiency	10 lm/W
External Quantum Efficiency	5.3 %
CIE 1931 at 100 cd/m ²	(0.50 / 0.49)
DC lifetime at 100 cd/m ² at RT	>220000 h
AC lifetime at 200 cd/m ² at RT	11000 h

Sample preparation

- 5g/l in toluene or anisole for spin-coating / ready to use formulation is available
- Special formulation needed for inkjet
- Preparation of device should be in N₂ atmosphere

Absorption spectrum & EL



- 1 Merck does not guarantee the same performance will be measured at customer
- 2 The device structure can be changed according to customer's requirements
- 3 Baytron® P

We provide information and advice to our customers on application technologies and regulatory matters to the best of our knowledge and ability, but without obligation or liability. Existing laws and regulations are to be observed in all cases by our customers. This also applies in respect to any intellectual property rights of third parties, including patents and trademarks. Our information and advice do not relieve our customers of their own responsibility for checking the suitability of our products for the envisaged purpose or the necessity of obtaining any applicable intellectual property licenses.

Make it bright.
livilux® - OLED Materials